

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 7779-3-2 (1980): Schedule for Properties and Availability of Stones for Construction Purposes, Part III: Tamil Nadu State, Section 2: Engineering Properties of Building Stones [CED 6: Stones]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



Indian Standard

SCHEDULE FOR PROPERTIES AND
AVAILABILITY OF STONES FOR
CONSTRUCTION PURPOSES

PART III TAMIL NADU STATE

Section 2 Engineering Properties of Building Stones

UDC 691.21-002-611 (548.1)



© Copyright 1980

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

July 1980



G 7 2

Indian Standard

SCHEDULE FOR PROPERTIES AND AVAILABILITY OF STONES FOR CONSTRUCTION PURPOSES

PART III TAMIL NADU STATE

Section 2 Engineering Properties of Building Stones

Stones Sectional Committee, BDC 6

Chairman

SHRI B. RAMACHANDRAN

Representing

Geological Survey of India

Members

SHRI S. R. PRADHAN (*Alternate to*
Shri B. Ramachandran)

SHRI K. K. AGRAWALA Builders' Association of India, Bombay

SHRI K. K. MADHOK (*Alternate*)

SHRI S. K. BANERJEE National Test House, Calcutta

SHRI P. R. DAS (*Alternate*)

SHRI R. K. BANSAL Delhi Marble Dealers' Association, New Delhi
SHRI J. K. CHARAN Engineer-in-Chief's Branch (Ministry of
Defence)

SHRI K. KAMLANATHAN (*Alternate*)

CHIEF ARCHITECT Central Public Works Department, New Delhi
CHIEF ENGINEER (B & R) Public Works Department, Government of
Rajasthan, Jaipur

SHRI Y. N. DAVE Department of Geology & Mining, Government
of Rajasthan, Udaipur

SHRI R. G. GUPTA (*Alternate*)

DEPUTY DIRECTOR (RESEARCH), Public Works Department, Government of Uttar
PWD RESEARCH INSTITUTE Pradesh, Lucknow

DR M. P. DHIR Central Road Research Institute (CSIR), New
Delhi

DR N. B. LAL (*Alternate*)

(Continued on page 2)

© Copyright 1980

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

(Continued from page 1)

Members

DIRECTOR (CSMRS)
DEPUTY DIRECTOR (CSMRS)
(Alternate)

SHRI M. K. GUPTA
DR IQBAL ALI

SHRI G. RAMAKRISHNA (Alternate)
SHRI R. C. JAIN
SHRI R. G. LIMAYE
DR G. S. MEHROTRA

DR DINESH CHANDRA (Alternate)
SHRI PREM SWARUP

SHRI A. K. AGARWAL (Alternate)
DR A. V. R. RAO
SHRI J. SEN GUPTA (Alternate)
RESEARCH OFFICER, GERI,
VADODARA
RESEARCH OFFICER MERI, NASIK

SUPERINTENDING ENGINEER
(DESIGNS)
SUPERINTENDING ENGINEER
(DESIGNS)
DY CHIEF ENGINEER (I & D)
(Alternate)
SUPERINTENDING ENGINEER
(PLANNING CIRCLE)
SHRI D. AJITHA SIMHA,
Director (Civ Engg)

Representing

Central Water Commission, New Delhi

Himalayan Tiles and Marble Pvt Ltd, Bombay
Engineering Research Laboratories, Government
of Andhra Pradesh, Hyderabad

Ministry of Shipping & Transport (Roads Wing)
Indian Institute of Technology, Bombay
Central Building Research Institute (CSIR),
Roorkee

Department of Geology & Mining, Government of
Uttar Pradesh, Lucknow

National Buildings Organisation, New Delhi

Public Works Department, Government of
Gujarat, Ahmadabad

Irrigation & Power Department, Government of
Maharashtra, Bombay

Public Works & Electricity Department,
Government of Karnataka, Bangalore

Public Works Department, Government of Tamil
Nadu, Madras

Public Works Department, Government of West
Bengal, Calcutta

Director General, ISI (Ex-officio Member)

Secretary

SHRI S. SENGUPTA
Assistant Director (Civ Engg), ISI

Indian Standard

SCHEDULE FOR PROPERTIES AND AVAILABILITY OF STONES FOR CONSTRUCTION PURPOSES

PART III TAMIL NADU STATE

Section 2 Engineering Properties of Building Stones

0. F O R E W O R D

0.1 This Indian Standard (Part III/Sec 2) was adopted by the Indian Standards Institution on 29 February 1980, after the draft finalized by the Stones Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 Stones are available in large quantities in different parts of the country. To choose and utilize them for various purposes, it is necessary to know their availability as well as their various physical properties. Accordingly this standard is formulated to cover such information. It is hoped that with the publication of this standard it would be convenient for the users to know the location of various types of stone, and it would also act as a guide for their proper selection depending upon their particular use. This standard will give a general information for prospective builders who use stone and stone aggregates. The final acceptance of these materials in any work would, however, be subject to the physical standards and other specifications and quality control requirements stipulated for individual works.

0.2.1 This standard is being published in parts, each part covering one State. For facility in compilation and use of the standard, each part is divided in three sections. Accordingly Part III covers Tamil Nadu State and is being issued in three sections.

0.3 The information contained in this section is based on the data provided by Public Works Department, Government of Tamil Nadu and covers data collected up to the end of 1979. Further information as and when available will be published as addendum to this standard.

0.4 In reporting the results of a test or analysis made in accordance with this standard, if the final value, observed or calculated is to be rounded off, it shall be done in accordance with IS : 2-1960*.

1. SCOPE

1.1 This standard (Part III/Sec 2) covers engineering properties of building stones of Tamil Nadu State.

2. TEST RESULTS

2.1 The test results of various types of building stones tested for some of the important properties according to relevant Indian Standards are given in Table 1.

*Rules for rounding off numerical values (*revised*).

TABLE 1 TEST RESULTS OF ENGINEERING PROPERTIES OF BUILDING STONES — TAMIL NADU STATE

(Clause 2.1)

Sl. No.	LOCATION	ROCK TYPE	COLOUR (IS : 1123-1975*)	STRUCTURE AND TEXTURE (IS : 1123-1975*)	APPARENT SPECIFIC GRAVITY (IS : 1124-1974†)	WATER ABSORPTION, PERCENT (IS : 1124-1974†)	COMPRESSIVE STRENGTH kg/cm ² [IS : 1121 (PART I)-1974†]				TRANSVERSE STRENGTH kg/cm ² [IS : 1121 (PART II)-1974§]		DURABILITY, PERCENT LOSS (IS : 1126-1974)	REMARKS
							Tested Saturated Surface Dry		Tested Dry		Tested in Wet Condition	Tested in Dry Condition		
							Parallel to grain	Perpendi- cular to grain	Parallel to grain	Perpendi- cular to grain				
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)
I COIMBATORE DISTRICT														
1.	Amaravathi Nagar	Biotite gneiss	Leucocratic	Gneissic, hypidiomorphic medium grained	2.65	0.46	—	555.50	—	—	164.50	—	2.81	Low compressive strength due to the presence of biotite
2.	Coimbatore	Hornblende biotite gneiss	do	Gneissic, hypidiomorphic coarse grained	2.64	0.21	—	682.40	—	—	134.00	—	0.32	—
3.	Parambikulam Aliyar	Charnockite	do	Massive, hypidiomorphic fine grained	2.69	0.55	—	813.60	—	—	163.00	—	0.84	—
4.	Sholayar Nagar	Hornblende biotite gneiss	do	Grambitic, foliated, hypidiomorphic medium grained	2.66	0.50	—	948.20	—	—	95.48	—	4.47	—
II CHINGLEPUT DISTRICT														
5.	Tiruttani	Biotite granite	Leucocratic	Massive, hypidiomorphic medium grained	2.68	0.81	—	580.70	—	—	176.00	—	0.59	Low compressive strength due to the predominance of biotite
6.	Tiruttani	do	do	Massive, hypidiomorphic coarse grained	2.63	0.70	—	798.90	—	—	191.00	—	9.54	—
III KANYAKUMARI DISTRICT														
7.	Andoor Quarry Kalkulam Taluk	Genetiferous biotic gneiss	Leucocratic	Gneissic, hypidiomorphic medium grained	2.86	0.47	—	357.61	—	551.06	177.95	177.97	1.97 (20 cycles) 2.34 (34 cycles)	Low compressive strength due to predominance of granite and biotite

(Continued)

TABLE 1 TEST RESULTS OF ENGINEERING PROPERTIES OF BUILDING STONES — TAMIL NADU STATE — *Contd*

Sl. No.	LOCATION	ROCK TYPE	COLOUR (IS : 1123-1975*)	STRUCTURE AND TEXTURE (IS : 1123-1975*)	APPARENT SPECIFIC GRAVITY (IS : 1124-1974†)	WATER ABSORPTION, PERCENT (IS : 1124-1974†)	COMPRESSIVE STRENGTH kg/cm ² [IS : 1121 (PART I)-1974‡]				TRANSVERSE STRENGTH kg/cm ² [IS : 1121 (PART II)-1974§]		DURABILITY, PERCENT LOSS (IS : 1126-1974)	REMARKS
							Tested Surface Dry		Tested Dry		Tested in Wet Condition	Tested in Dry Condition		
							Parallel to grain	Perpendicular to grain	Parallel to grain	Perpendicular to grain				
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)
8.	Cheruppalur	Biotite granite	Leucocratic	Massive, hypidiomorphic medium grained	2.67	0.59	—	791.80	—	—	108.00	—	5.23	—
9.	Tiruvettar	Charnockite	Leucocratic grey	do	2.79	0.22	—	738.20	—	—	198.00	—	1.17	—
IV MADURAI DISTRICT														
10.	Manjalar Dam Devanampatti	Charnockite	Leucocratic brownish grey	Granular, hypidiomorphic medium grained	2.76	0.28	—	707.50	—	—	159.20	—	1.21	—
11.	Manjalar Dam	do	Leucocratic light grey	Foliated, hypidiomorphic medium grained	2.68	0.19	—	692.20	—	—	221.90	—	1.75	—
12.	Manjalar Dam	do	Leucocratic	Massive, hypidiomorphic coarse grained	2.71	0.20	—	626.60	—	—	245.00	—	1.17	—
13.	Manjalar Dam	Genetiferous gneiss	Leucocratic pinkish	Foliated, gneissic, hypidiomorphic coarse grained	2.64	—	—	760.00	—	—	—	—	3.97	—
14.	Madurai	Granite	Leucocratic	Massive, hypidiomorphic coarse grained	2.62	0.38	—	700.40	—	—	103.50	—	1.92	—
V NORTH ARCOT DISTRICT														
15.	Sathanur	Charnockite	Leucocratic bluish grey	Massive, hypidiomorphic medium grained	2.73	—	—	810.40	—	—	—	—	0.39	—

(Continued)

TABLE 1 TEST RESULTS OF ENGINEERING PROPERTIES OF BUILDING STONES — TAMIL NADU STATE — *Contd*

Sl No.	LOCATION	ROCK TYPE	COLOUR (IS : 1123-1975*)	STRUCTURE AND TEXTURE (IS : 1123-1975*)	APPARENT SPECIFIC GRAVITY (IS : 1124-1974†)	WATER ABSORPTION, PERCENT (IS : 1124-1974†)	COMPRESSIVE STRENGTH kg/cm ² [IS : 1121 (PART I)-1974‡]				TRANSVERSE STRENGTH kg/cm ² [IS : 1121 (PART II)-1974§]		DURABILITY, PERCENT LOSS (IS : 1126-1974)	REMARKS
							Tested Surface Dry		Tested Dry		Tested in Wet Condition	Tested in Dry Condition		
							Parallel to grain	Perpendi- cular to grain	Parallel to grain	Perpendi- cular to grain				
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)
VI BAMNAD DISTRICT														
16.	Aruppukottai	Biotite granite gneiss	Leucocratic pink	Gneissic, massive, hypidiomorphic medium grained	2.62	0.28	—	761.10	—	—	195.00	—	0.30	—
17.	Aruppukottai	Pink granite	Leucocratic	Massive, hypidiomorphic medium grained	—	—	501.90	569.90	738.20	826.80	170.04	235.61	—	—
18.	Aruppukottai	Charnockite	Mesocratic grey	do	—	—	807.10	915.30	620.10	836.63	215.36	181.30	0.30 (20 cycles) 0.53 (30 cycles)	—
19.	Kundrakudi	Pink granite	Leucocratic	do	—	—	383.87	413.35	255.90	305.05	102.76	122.32	—	—
20.	Mandapam Camp	Coral	do	Coralline,	1.14	30.66	—	156.40	—	—	—	39.80	4.00	—
21.	Srivilliputhur	Charnockite	Leucocratic grey	Massive, hypidiomorphic medium grained	2.67	0.59	406.80	458.90	246.00	488.70	196.93	174.00	1.28 (20 cycles) 1.57 (30 cycles)	—
22.	Thirumelai Quarry Sivaganga	Granite gneiss	Leucocratic	Gneissic, foliated, hypidiomorphic medium grained	—	—	244.54	265.09	515.53	662.00	158.10	152.61	—	Disintegrated after 10 cycles
23.	Va chiyur Quarry Sivaganga	do	do	do	—	—	277.39	456.02	564.79	656.19	138.16	130.50	—	Disintegrated after 9 cycles
VII SALEM DISTRICT														
24.	Kondampatti Village Namakkal Taluk	Charnockite	Mesocratic	Massive, hypidiomorphic	2.85	0.24	—	1 266.46	—	1 053.19	218.81	201.54	0.25 (20 cycles) 0.34 (30 cycles)	—
25.	Uttambadi Quarry Namakkal Taluk	do	do	Massive, hypidiomorphic medium grained	2.99	0.34	—	736.26	—	753.63	205.62	221.46	0.28 (20 cycles) 0.39 (30 cycles)	—
(Continued)														

(Continued)

TABLE 1 TEST RESULTS OF ENGINEERING PROPERTIES OF BUILDING STONES — TAMIL NADU STATE — Contd

Sl. No.	LOCATION	ROCK TYPE	COLOUR (IS : 1123-1975*)	STRUCTURE AND TEXTURE (IS : 1123-1975*)	APPARENT SPECIFIC GRAVITY (IS : 1124-1974†)	WATER ABSORPTION, PERCENT (IS : 1124-1974†)	COMPRESSIVE STRENGTH kg/cm ² [IS : 1121 (PART I)-1974‡]				TRANSVERSE STRENGTH kg/cm ² [IS : 1121 (PART II)-1974§]		DURABILITY, PERCENT LOSS (IS : 1126-1974)	REMARKS
							Tested Saturated Surface Dry		Tested Dry		Tested in Wet Condition	Tested in Dry Condition		
							Parallel to grain	Perpendicular to grain	Parallel to grain	Perpendicular to grain				
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)
VIII SOUTH ARCOT DISTRICT														
26.	Kallakurichi	Charnockite	Mesocratic	Massive, hypidiomorphic medium grained	2.68	0.24	—	636.51	—	708.80	—	—	0.65 (20 cycles) 0.76 (30 cycles)	—
27.	Peramakal Quarry Tindivanam Taluk	do	do	do	2.76	0.27	—	954.70	—	782.50	237.76	304.50	0.99 (20 cycles) 1.23 (30 cycles)	—
28.	Tiruvakari Quarry Tindivanam Taluk	Granite	Leucocratic	do	3.04	0.13	—	690.44	—	706.77	174.25	161.09	0.80 (20 cycles) 1.11 (30 cycles)	—
29.	Tiruvakkarai Quarry Tindivanam Taluk	Charnockite	Mesocratic	do	2.81	0.24	—	398.31	—	410.12	292.64	225.41	0.89 (20 cycles) 1.25 (30 cycles)	—
30.	Tirukoilur Anthibi + Quarry	Granite	Leucocratic	do	2.64	0.38	—	663.37	—	830.99	126.37	122.59	1.99 (20 cycles) 2.77 (30 cycles)	—
IX TIRUNELVELI DISTRICT														
31.	Ambasamudram	Charnockite	Mesocratic	Massive, hypidiomorphic medium grained	—	—	351.52	515.55	451.13	456.99	143.91	157.10	0.60 (20 cycles) 0.70 (30 cycles)	—
32.	Manimuthar Tirunelveli	do	Leucocratic bluish grey	do	2.66	0.40	574.17	928.63	495.06	749.93	303.19	234.64	1.89 (20 cycles) 2.19 (30 cycles)	—
X TIRUCHI DISTRICT														
33.	Easini Quarry Perambalur Taluk	Charnockite	Mesocratic	Massive, hypidiomorphic	2.77	0.22	—	544.61	672.59	—	—	—	0.96 (20 cycles) 12.5 (30 cycles)	—

*Method of identification of natural building stones (first revision).

†Method of test for determination of water absorption, apparent specific gravity and porosity of natural building stones (first revision).

‡Method of test for determination of strength properties of natural building stones: Part I Compressive strength (first revision).

§Method of test for determination of strength properties of natural building stones: Part II Transverse strength (first revision).

||Method of test for determination of durability of natural building stones (first revision).